



experience,
trust, service

800-BLAST-IT
www.marcousa.com


Davenport, IA • Harrisburg, PA • Houston, TX • Savannah, GA • Shreveport, LA

Autofax #00093710

Updated: 07/03/06

page 1 of 4

SAE SPECIFICATION J827 - HIGH CARBON STEEL SHOT

 <p>SAE The Engineering Society For Advancing Mobility Land Sea Air and Space INTERNATIONAL 480 Commonwealth Drive, Warrendale, PA 15096-0001</p>	SURFACE VEHICLE RECOMMENDED PRACTICE	SAE J827	REV. SEP1996
		Issued 1962-06 Revised 1996-09	
		Superseding J827 JUL94	

1. Scope

This SAE Recommended Practice describes chemical composition and physical characteristic requirements for high-carbon cast-steel shot to be used for shot peening or blast cleaning operations.

2. References

2.1 Applicable Publications - The following publications form a part of this specification to the extent specified herein. The latest issue of SAE, ASTM and ISO publications shall apply.

2.1.1 - SAE Publications - Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001

- SAE J444 - Cast Shot and Grit Size Specifications for Peening and Cleaning
- SAE J445 - Metallic Shot and Grit Mechanical Testing

2.1.2 - ASTM Publications - Available from ASTM, 100 Barr Harbor, West Conshohocken, PA 19428-2959

- ASTM B 215, Method B - Methods of Sampling Finished Lots of Metal Powders
- ASTM E 140 - Hardness Conversion Tables for Metals (Relationship Between Brinell Hardness, Vickers Hardness, Rockwell Hardness, Rockwell Superficial Hardness and Knoop Hardness)
- ASTM E 384 - Test method for Microhardness of Materials

2.2 - Related Publications - The following publications are provided for information purposes only and are not a required part of this document.

2.2.1 - ISO Publications - Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002

- ISO 11124 Part 3 - High-carbon cast-sheet steel shot and grit
- ISO 11125 Part 1 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 1: Sampling
- ISO 11125 Part 2 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 2: Determination of particle size distribution
- ISO 11125 Part 3 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 3: Determination of hardness
- ISO 11125 Part 4 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 4: Determination of apparent density
- ISO 11125 Part 5 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 5: Determination of percentage defective particles and microstructure.
- ISO 11125 Part 6 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 6: Determination of foreign matter
- ISO 11125 Part 7 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 7: Determination of moisture

3. Description

High-carbon cast-steel shot is obtained by atomizing molten steel. The shot is heat treated and screened to produce a range of sizes from HCS S70 to HCS S1320 or larger as described in SAE J444. Other sizes are available.

4. Size Classification

Cast-steel shot shall be identified by HCS S for shot, followed by three numbers representing the size in ten thousandths of inches, in accordance with SAE J444.

Example: HCS330 indicates a cast-steel shot identified by a nominal sieve opening of 050mm (0.0331 in).

5. Chemical Composition

The finished shot shall have the chemical composition shown in Table 1:

TABLE 1 - CHEMICAL COMPOSITION

Element	Weight Percent
Carbon	0.85 - 1.2%
Manganese	
HCS S70 to HCS S110	0.35 - 1.2%
HCS S170	0.5 - 1.2%
HCS S230 and up	0.6 - 1.2%
Silicon	0.4% minimum
Sulfur	0.050% maximum
Phosphorous	0.050% maximum

6. Hardness

6.1 - Standard Hardness - The hardness of 90% of all shot particles shall be within the range of 40 to 51 HRC.

6.2 - Special Hardness - Shot for peening and blast cleaning is manufactured from 40 to 65 HRC. The user may specify a range to suit the application. The minimum hardness range that can be specified is 7 points HRC.

7. Microstructure

The microstructure of high-carbon cast-steel shot shall be uniform martensite, tempered to a degree consistent with the hardness range, with fine, well distributed carbides, if any.

8. General Appearance

High-carbon cast-steel shot is generally spherical and shall have no more than 20% of the particles with objectionable characteristics. Any one particle tested that has more than one different defect shall only be counted as one.

8.1 - Objectionable Characteristics

8.1.1 - Particle Shape - No more than 5% of the particles in a shot sample shall be elongated. An elongated particle is one whose length is in excess of twice the maximum particle width.

8.1.2 - Voids - No more than 10% of the particles in a sample shall contain objectionable voids. Such a void is a smooth-surfaced, internal hole whose cross-sectional area is larger than 10% of the cross-section area of the particle.

8.1.3 - Shrinkage - No more than 10% of the particles in a sample shall contain objectionable shrinkage. Such a shrinkage is an internal cavity with an irregular dendritic surface whose area is larger than 40% of the particle area.

8.1.4 - Cracks - No more than 15% of the particles in a shot sample shall contain objectionable cracks. Such a crack is a linear discontinuity longer than three times its width, longer than 20% of the shortest cross section of the particle and radial in orientation.

8.1.5 - Microstructure - Carbide networks, partial decarburization, grain boundary segregation or pearlite are undesirable. No more than 15% of the particles tested shall contain these defects.

8.1.6 - Nonmagnetic Material - No more than 1% of the shot sample, by weight, shall be of nonmagnetic material.

9. Density

The density of high-carbon cast-steel shot shall be not less than 7 g/cm³

10. Inspection Procedure

10.1 - Sampling - Samples for testing shall be representative of each shipment or production lot. The method of sampling shall be ASTM B 215, Method B.

10.2 - Sample Mounting for Testing - Shot samples used for testing for hardness, microstructure and objectionable defects shall be mounted one layer deep in bakelite or other suitable strong metallurgical sample mounting media.

The mounted sample shall be ground to the center of the particles and polished by methods acceptable for microscopic examination. When grinding and polishing the sample, care must be taken not to overheat the sample and affect the microstructure and/or hardness.

10.3 - Hardness Testing - Hardness measurements shall be taken at the half radius on a minimum of 10 particles in the mounted sample.

The hardness shall be determined by using ASTM E 384 and using a 500 g load for sizes HCS S280 and finer, and 500 or 1000 g load for sizes HCS S330 and larger. Other microhardness test methods may be used as long as a reliable hardness conversion can be obtained by calibrating the test machine against known standards. Approximate conversion to Rockwell C Hardness Numbers can be obtained from ASTM 140 and from manufacturers of hardness testers.

10.4 - Microstructure - The mounted and polished sample shall be etched with 2% Nital or other suitable etchant and examined at approximately 500X magnification.

10.5 - Objectionable Characteristics - Objectionable characteristics shall be examined at 10X magnification. A minimum of 50 particles contained in the mount shall be evaluated.

10.6 - Density - Density shall be determined by placing 50 mL of water or alcohol in a 100 mL graduate, adding 100 g of shot and recording the increase in volume. Dividing 100 g by the volume increase will give the density in g/cm³. A pycnometer method may be used for more critical density measurements.

10.7 - Nonmagnetic Material - A hand magnet will be used to separate the magnetic shot from the nonmagnetic contaminants. The nonmagnetic contaminants shall be weighed and their percentage of the original sample weight calculated.

10.8 - Chemical Analysis - Any suitable ASTM Analytical procedure for steel may be used to test chemical composition.

10.9 - Mechanical Tests - See SAE J445 for methods of checking uniformity of shipments of shot.

11. Notes

11.1 - Marginal Indicia - The change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions have been made to the previous issue of the report. An (R) symbol to the left of the document title indicates a complete revision of the report.

Rationale

Not applicable.

Relationship of SAE Standard to ISO Standard

Not applicable.

Applications

This SAE Recommended Practice describes chemical composition, hardness, microstructure and physical characteristic requirements for high carbon cast steel shot to be used for shot peening or blast cleaning operations.

Reference Section

- SAE J444 - Cast Shot and Grit Size Specifications for Peening and Cleaning
 - SAE J445 - Metallic Shot and Grit Mechanical Testing
 - ASTM B 215, Method B - Methods of Sampling Finished Lots of Metal Powders
 - ASTM E 140 - Hardness Conversion Tables for Metals (Relationship Between Brinell Hardness, Vickers Hardness, Rockwell Hardness, Rockwell Superficial Hardness and Knoop Hardness)
 - ASTM E 384 - Test method for Microhardness of Materials
 - ISO 11124 Part 3 - High-carbon cast-sheet steel shot and grit
 - ISO 11125 Part 1 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 1: Sampling
 - ISO 11125 Part 2 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 2: Determination of particle size distribution
 - ISO 11125 Part 3 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 3: Determination of hardness
 - ISO 11125 Part 4 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 4: Determination of apparent density
 - ISO 11125 Part 5 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 5: Determination of percentage defective particles and microstructure.
 - ISO 11125 Part 6 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 6: Determination of foreign matter
 - ISO 11125 Part 7 - Preparation of steel substrates before application of paints and related products - Test methods for metallic abrasives - Part 7: Determination of moisture
-

Disclaimer

SAE Technical Standards Board Rules that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary and its applicability and suitability for any particular use, including and patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised or cancelled. SAE invites your written comments and suggestions.

Questions regarding this document: (724) 772-8512 • Fax (724) 776-0243
To place a document order: (724) 776-4970 • (724) 776-0790
SAE web address: <http://www.sae.org>



For more information call:

800-BLAST-IT

Phone: 800-252-7848
Fax: 563-324-6258
e-mail: sales@marcouisa.com
www.marcouisa.com

